



Version: 26 August 2022

RUTHUNA[®]

491 / 492 / 493

RUTHENIUM ALLOY ELECTROLYTES



Sustainable palladium substitute with significant price advantages

The ruthenium electrolytes RUTHUNA[®] 491, 492 and 493 are neutral electrolytes from which decorative gray ruthenium coatings can be deposited. The electrolytes are easy to operate, and the deposits have a high color constancy and retain their brightness.

RUTHUNA[®] is used both as a final layer for decorative applications, e.g. on buttons, zippers and accessories in the apparel industry, and as a corrosion-resistant intermediate layer, e.g. to replace palladium. But functional properties, such as reduced sparking in current-conducting applications, also speak in favor of using RUTHUNA[®]. For example, the process is recommended for the following technical applications: Reed switches, injet printer foils, surfaces of catalytic converters, electrolytic electrodes.

In contrast to strongly acidic electrolytes, where pre-gold plating, or pre-coating with palladium or palladium-nickel is mandatory, materials such as copper, nickel, brass or bronze alloys can be used as undercoats under the ruthenium layer. Of course, palladium, palladium alloy and gold layers can also serve as base materials.



Advantages

- Easy electrolyte maintenance
- High color consistency
- Brightness-preserving
- As corrosion-resistant intermediate layers as a substitute for palladium
- Copper, nickel, brass or bronze alloys can be used as undercoats

Applications

- Zippers
- Buttons
- Jewelry
- Reed switches
- Injet printer foils
- Catalyst surfaces
- Electrolysis electrodes

RUTHUNA® 491 / 492 / 493

RUTHENIUM ALLOY ELECTROLYTES

TECHNICAL SPECIFICATIONS

	RUTHUNA® 491	RUTHUNA® 492	RUTHUNA® 493
Ruthenium Content	10 g/l	5 g/l	5 g/l
Alloy Composition	100 % Ruthenium	94 % Ruthenium 6 % Nickel	90 % Ruthenium 10 % Cobalt
pH value 7 = neutral	7.0	7.3	6.0
Temperature for deposition	45 - 55 °C	45 °C	50 °C
Max. Layer Thickness Crack-free	0.8 µm	0.7 µm	1.0 µm
Plating Speed Deposition on substrate	0.04 µm/min @ 5 ASD/45°C 0.07 µm/min @ 5 ASD/55°C	0.04 µm/min @ 2.0 A/dm ²	0.08 µm/min @ 3.0 A/dm ²
L*a*b* Values Color values	74 / 0.9 / 4.0	73 / 0.9 / 4.3	68 / 1.0 / 3.5

YOUR CONTACT

Do you have a specific question or would you like a no-obligation quote calculation?
Our specialist will be happy to help you with any technical questions you might have.



Markus Legeler
Manager Sales International

Mail: markus.legeler@eu.umicore.com
Phone: +49 (0) 7171 607 - 204

